



(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
20.03.1996 Bulletin 1996/12

(21) Application number: **89909323.1**

(22) Date of filing: **07.08.1989**

(51) Int Cl.⁶: **C03C 12/00**, C03C 3/078,
C03C 3/085, C03C 3/087,
C03C 3/089, C03C 3/091,
C03C 3/093, C03C 3/097,
C03C 3/112, C03C 3/115

(86) International application number:
PCT/US89/03382

(87) International publication number:
WO 90/02102 (08.03.1990 Gazette 1990/06)

(54) **HOLLOW GLASS SPHERES**
HOHLGLASKUGEL
SPHERES CREUSES EN VERRE

(84) Designated Contracting States:
AT BE CH DE FR GB IT LI LU NL SE

(30) Priority: **24.08.1988 US 236042**

(43) Date of publication of application:
12.06.1991 Bulletin 1991/24

(73) Proprietor: **POTTERS INDUSTRIES, INC.**
Parsippany New Jersey 07054 (US)

(72) Inventors:
• **GOETZ, Kenneth, E.**
Maplewood, NJ 07040 (US)
• **HAGARMAN, James, A.**
Audubon, PA 19407 (US)
• **GIOVENE, Joseph, P., Jr.**
Belleville, NJ 07109 (US)

(74) Representative: **Goddard, Heinz J., Dr. et al**
FORRESTER & BOEHMERT
Franz-Joseph-Strasse 38
D-80801 München (DE)

(56) References cited:
EP-A- 0 276 921 **JP-B- 4 937 565**
US-A- 3 365 318 **US-A- 3 429 721**
US-A- 3 519 446 **US-A- 4 661 137**

- **CHEMICAL ABSTRACTS**, vol. 107, no. 14, 05 October 1987 Columbus, Ohio, USA page 275; ref. no. 119955H & SU-A- 1315403
- **GLASS AND CERAMICS**, vol. 45, no. 8, August 1988, NEW YORK US pages 289 - 291; V.V.BUDOV ET AL.: "CHOICE OF GLASS COMPOSITION FOR PRODUCING HOLLOW MICROSPHERES."
- **CHEMICAL ABSTRACTS**, vol. 88, no. 26, 26 June 1978 Columbus, Ohio, USA page 324; ref. no. 196379Q & SU-A- 601242
- **CHEMICAL ABSTRACTS**, vol. 109, no. 2, 11 July 1988 Columbus, Ohio, USA page 261; ref. no. 10650V & DD-A- 251967
- **M.B. VOLF**, "Chemical Approach to Glass", (7), 1984, Elsevier, New York, pp. 219-221, 229, 418-421, 408-418

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

DescriptionFIELD OF THE INVENTION

5 This invention relates to hollow glass spheres made by heating solid glass particles.

BACKGROUND OF THE INVENTION

10 Hollow glass spheres are widely used in industry as additives to polymeric compounds, e.g., as modifiers, enhancers, rigidifiers and fillers. Generally, it is desirable that these spheres be strong to avoid being crushed or broken during further processing of the polymeric compound, such as by high pressure spraying, kneading, extrusion or injection molding. It also is desirable in many cases that these spheres have densities close to that of the polymeric compound into which they are introduced in order that they distribute evenly within the compound upon introduction and mixing. Furthermore, it is desirable that these spheres be resistant to leaching or other chemical interaction with their associated
15 polymeric compound.

The method of expanding solid glass particles into hollow glass spheres by heating is well known. See, e.g., U.S. Pat. No. 3,365,315. Glass is ground to particulate form and then heated to cause the particles to become plastic and for gaseous material within the glass to act as a blowing agent to cause the particles to expand. During heating and expansion, the particles are maintained in a suspended state either by directing gas currents under them or allowing
20 them to fall freely through a heating zone. Sulfur, or compounds of oxygen and sulfur, serves as the principal blowing agent.

A number of factors affect the density, size, strength, chemical durability and yield (the percentage by weight or volume of heated particles that become hollow) of hollow glass spheres. These factors include the chemical composition of the glass; the sizes of the particles fed into the furnace; the temperature and duration of heating the particles; and
25 the chemical atmosphere (e.g., oxidizing or reducing) to which the particles are exposed during heating.

There have been problems in attempting to improve the quality and yield of hollow glass spheres. One reason is that it was believed, see for example US-PS 3,365,315, JP-Publ. No. 49/37565, US-PS 4,391,646, US-PS 4,661,137, "Glass and Ceramics, vol. 45, no. 8, pages 289 to 291" and EP 0 276 921 A1, that the percentage of silica (SiO_2) in glass used to form hollow glass spheres should be between 65 and 85 percent by weight and that a weight percentage of
30 SiO_2 below 60 to 65 percent would drastically reduce the yield of the hollow spheres. For example, the composition discussed in US-PS 4,661,137 contained either 67.75 or 71.4 weight percentage SiO_2 and 0.01 or 0.05 weight percentage sulfur, the teaching of US-PS 4,661,137 being that compositions of very slight sulfur contents, less than 0.01 weight percentage, give particles having a very high resistance to hydrostatic pressure, as the slight amount of sulfur results in diminished expansion of the particles at high density. According to "Glass and Ceramics, vol. 45, no. 8, pages 289 to 291", giving a further example of the prior art prejudice, it is sensible to produce microsphere glasses of a total concentration of B_2O_3 and SiO_2 of not less than 70 %.

Also, the prior art has overlooked the significant improvement in strength of hollow glass spheres achieved through the optimization of particle size.

40 OBJECTS AND SUMMARY OF THE INVENTION

Accordingly, it is an object of the present invention to provide an improved yield of hollow glass spheres from glass particles.

Another object of the invention is to provide hollow glass spheres which permit the use of a wider range of materials. Particularly, the invention has the object of providing improved hollow glass spheres having a content of silica between
45 50 and 57 percent.

It is a further object of this invention to provide hollow glass spheres which exhibit high strength and resistance to crushing or breaking. Also, the invention has the object of providing hollow glass spheres highly resistant to chemical decomposition or leaching.

50 It is yet another object of the invention to provide hollow glass spheres of selected average density having a range of sizes which provide optimum average strength.

It is still a further object of this invention to provide hollow glass spheres having average densities ranging from .10 grams per cubic centimeter to 2.0 grams per cubic centimeter. Also, the invention has the object of providing hollow glass spheres having average densities generally matching the polymeric compounds into which they are introduced.

55 It is still another object of the invention to provide polymeric composites containing hollow glass spheres as aforesaid.

These objects are met by the present invention.

The present invention provides hollow glass spheres which exhibit greater average strength and resistance to crushing or breaking than commercial glass spheres of comparable average density. These glass spheres also are highly

resistant to chemical decomposition or leaching which enables them to be used with a wide range of polymeric compounds. The yield of hollow glass spheres of the present invention also is very high.

The high strength, chemical resistivity and yield of the hollow glass spheres of the present invention is the result of a new composition of glass. The strength of these spheres also is the result of optimally selecting the range of sizes of particles comprising the final product. We have found that for a product of hollow glass spheres of a particular desired average density, there is an optimum range of sizes of particles making up that product which produces the maximum average strength.

The hollow glass spheres of the present invention can be produced with average densities ranging from approximately .10 grams per cubic centimeter to approximately 2.0 grams per cubic centimeter (solid glass has an average density of approximately 2.5 grams per cubic centimeter). In several advantageous embodiments, these spheres comprise glass that contains the following ingredients (that may be present within the glass itself or the hollow cavity within the glass sphere) in the following amounts stated as weight percentages. (R represents a metal or an element like phosphorous which combines with oxygen in glass, R_2O being Na_2O , K_2O or Li_2O and RO being CaO or ZnO .)

SiO_2	50-57
R_2O (alkali metal oxides)	2-15
B_2O_3	0-20
S	.05-1.5
RO	2-25
Al_2O_3	0-10
P_2O_5	0-5
F	0-5

Preferably, the glass has a substantially molar balance of said several alkali metal oxides, being Li_2O , Na_2O and K_2O , which has been found to improve chemical durability and resistance to leaching.

Glass particles of the present invention are heated to cause them to expand into hollow spheres. The heat may be applied using conventional methods such as a furnace. The furnace preferably provides a quantity of excess gas of between approximately 5 and 25 percent above a stoichiometric mixture of gas and air to provide a reducing atmosphere for the particles during heating.

The hollow glass spheres of the present invention can be used in a wide range of polymeric compounds, such as paints, coatings, plastisols, organasols, thermoplastic and thermosetting polymers, rigidifiers and spackling compounds. Because of their high strength and durability, these spheres can be incorporated into a wide range of polymers and subjected to the high pressures of extrusion and injection molding.

The present invention, including further objects, features and advantages, will be more fully understood from the following detailed description.

DESCRIPTION OF CERTAIN PREFERRED EMBODIMENTS

A central feature of the present invention is a new composition of glass used to produce hollow glass spheres. The principal ingredient in this glass is SiO_2 which is present in an amount between 50 and 57 weight percent.

An alkali metal oxide (R_2O) is included in the glass in an amount equal to between 2 and 15 weight percent. Preferably, R_2O comprises Na_2O , K_2O and Li_2O in weight percentages preferably ranging from 2.5 to 12.8, 3.8 to 10.0 and 1.0 to 3.0, respectively. Advantageously, each of these alkali metal oxides is included in the glass in a substantially molar balance for improved chemical durability and resistance to leaching. Such a balance is substantially achieved with a glass containing approximately one part by weight Li_2O , to two parts by weight Na_2O , to three parts by weight K_2O .

B_2O_3 is present in the glass in a weight percentage of between 0 and 20 to lower melting temperature and improve chemical durability. Preferably, the glass composition contains between 6 and 15 weight percent B_2O_3 .

A weight percentage of sulfur (as an individual element or in combination with another element such as oxygen as, e.g., SO_2 or SO_3) of between .05 and 1.5 is present in the glass to provide a blowing agent. If the parameters (time, duration and heating atmosphere) of heating the glass particles remain fixed, the density of the hollow glass spheres decreases as both the percentage of sulfur, or compounds of oxygen and sulfur, in the glass and the size of the feedstock

particles increase. By controlling average feedstock size and the percentage of sulfur in the glass, the glass spheres of the present invention can be produced with average densities ranging from .10 grams per cubic centimeter to 2.0 grams per cubic centimeter.

The glass contains RO in a weight percentage of between 2 and 25. Preferably, these oxides are CaO and ZnO and are present in the glass in weight percentages ranging from 5 to 20 and 1.5 to 4.0, respectively. These oxides improve the chemical durability and resistance to leaching of the glass. CaO, moreover, improves the workability and viscosity of the glass over a wider range of temperatures, and ZnO helps the glass to retain sulfur during its preparation.

RO₂ (other than SiO₂) can be present in the glass up to 5 weight percent. Preferably, however, it is omitted and is present only as an impurity.

R₂O₃ (other than B₂O₃) can be present in the glass up to 10 weight percent. Preferably, this oxide is Al₂O₃ and is present in a weight percentage of between 2 and 7. The presence of this oxide improves chemical durability and resistance to leaching.

R₂O₅ can be present in the glass up to 5 weight percent. Preferably, this oxide is P₂O₅ and is present in an amount ranging from .5 to 4 weight percent. A small amount of P₂O₅ is believed to reduce the glass' melting point and improve its workability.

Flourine can be present in the glass in an amount up to 5 weight percent. Preferably, flourine is present in a weight percentage ranging from 1.5 to 2.5. Flourine improves the workability and viscosity of the glass over a wider range of temperatures and is believed also to act as an additional blowing agent during glass expansion.

In certain preferred embodiments, the glass is prepared by introducing glass-forming materials into a crucible in amounts which will result in the desired glass composition after heating-and cooling. One of ordinary skill in the art could select appropriate amounts of glass-forming materials to prepare glass having the composition of this invention. After heating, the molten materials are quenched in water to produce a glass frit which is ground into the particles used to produce the hollow glass spheres.

The particles are heated and caused to expand in apparatus similar to that described in U.S. Patent Nos. 2,619,776 and 2,945,326. Preferably, the glass particles are air classified prior to heating using, for example, an Alpine American, Model 132 MP, air classifier, to provide a selected range of sizes of particles for feeding into the furnace to produce an optimum range of sizes of particles in the final glass-sphere product.

For a product of hollow glass spheres having a particular desired average density, there is an optimum range of sizes of particles making up that product which produces the maximum average strength. This range can be expressed by the following formula:

$$\frac{90P-10P}{50P} = GQ$$

$$.8 \leq GQ \leq 1.3$$

where 90P is the size for which 90% of the particles in the glass-sphere product are smaller (referred to as the 90th percentile size); 10P is the size for which only 10% of the particles in the glass-sphere product are smaller (referred to as the 10th percentile size); 50P is the size for which 50% of the particles in the glass-sphere product are smaller (referred to as the 50th percentile size); and GQ stands for the gradation quotient. We have found that in order to maximize the average strength of a product of hollow glass spheres having a selected average density, the sizes of particles making up that product should have a GQ of between .8 and 1.3. We have found that a GQ within this range maximizes the strength of the product independently of its chemical composition.

It should be understood that a product of hollow glass spheres can include both solid and hollow glass spheres. All the particles heated in the furnace do not expand, and most hollow glass-sphere products are sold without separating the hollow from the solid spheres.

The invention will be further understood from the following examples.

EXAMPLE 1

Molten glass was quenched in water to produce a glass frit having a chemical composition calculated as follows (amounts are indicated as weight percentages): 53.81% SiO₂; 4.29% Na₂O; 6.36% K₂O; 2.06% Li₂O; 11.74% B₂O₃; 1.37% SO₃; 10.64% CaO; 1.96% ZnO; 4.89% Al₂O₃; 0.98% P₂O₅; and 1.90% F₂. The glass was ground to particles and air classified to provide the following breakdown of sizes: 90% smaller than 46.5 μm (90P = 46.5 μm); 10% smaller than 15.2 μm (10P = 15.2 μm); and 50% smaller than 29.1 μm (50P = 29.1 μm). These particles were fed into a furnace at the rate of 1.13 Kg (2.5 pounds) per hour using 3.7 m³ (130 cubic feet) per hour of gas at a gas/air mixture which was approximately 12% excess gas (12% above a stoichiometric mixture). The resultant glass-sphere product had an average density of .22 grams per cubic centimeter at a yield of 92.6% by weight hollow glass spheres. Average density was determined by weighting a sample of the glass-sphere product and determining its volume with an air comparison pycnometer.

The breakdown of sizes of this glass-sphere product was as follows: 90P = 104 μm; 10P = 35.8 μm; and 50P = 66.1

µm. Accordingly, its gradation quotient (GQ = 90P - 10P/50P) was 1.03.

The strength of this glass-sphere product was determined by subjecting a sample to hydrostatic pressure and determining the percentage of volume loss. These percentages were as follows for the following hydrostatic pressures: 21.78% at 3.4 MPa (500 psi); 45.0% at 5.2 MPa (750 psi); and 58.6% at 6.9 MPa (1000 psi). By comparison, the strongest commercial glass-sphere product of comparable average density (.23 grams per cubic centimeter) lost 54% of its volume at 5.2 MPa (750 psi).

The chemical durability and resistance to leaching of this glass-sphere product was determined by subjecting a sample to boiling deionized water for one hour under reflux and then testing the conductivity, pH, sodium content and potassium content of the water. The results were as follows: conductivity = 61 mho/cm; ph = 8; sodium = 4.2 mg/liter; potassium = 8.8 mg/liter. By comparison, a commercial glass-sphere product of comparable density subjected to the same test produced the following results: conductivity = 200 mho/cm; ph = 8.8; sodium = 21.2 mg/liter; and potassium = 11.6 mg/liter.

EXAMPLE 2

A glass frit was prepared with a calculated chemical composition the same as Example 1. This frit was ground to provide a breakdown of particle sizes as follows: 90P = 19.8 µm; 10P = 3.6 µm; and 50P = 11.3 µm. These particles were fed into a furnace at the rate of 1.53 Kg (3.4 pounds) per hour with the furnace being fed gas at the rate of 3.4 m³ (120 cubic feet) per hour at a gas/air mixture which was approximately 9% excess gas. The resultant glass-sphere product had an average density of .30 grams per cubic centimeter at a yield of 98.4% by weight hollow spheres. This glass-sphere product was comprised of spheres having the following breakdown of sizes: 90P = 44.8 µm; 10P = 13.2 µm; and 50P = 29.5 µm. Accordingly, its GQ was 1.07.

The percentage volume loss of this product under hydrostatic pressure was as follows: 2% at 3.4 MPa (500 psi); 5% at 5.2 MPa (750 psi); and 11% at 6.9 MPa (1000 psi). By comparison, the strongest commercial product of comparable average density (.28 grams per cubic centimeter) had a percentage volume loss of 10% at 3.4 MPa (500 psi), 23% at 5.2 MPa (750 psi), and 35% at 6.9 MPa (1000 psi).

EXAMPLE 3

Molten glass was quenched in water to produce a glass frit having a chemical composition calculated as follows (amounts are indicated as weight percentages): 54.18% SiO₂; 2.66% Na₂O; 3.94% K₂O; 1.28% Li₂O; 11.82% B₂O₃; .69% SO₃; 15.64% CaO; 1.97% ZnO; 4.93% Al₂O₃; 0.99% P₂O₅; and 1.92% F₂. The frit was ground to provide particles having a breakdown of sizes as follows: 90P = 17.1 µm; 10P = 6.0 µm; and 50P = 11.3 µm. These particles were fed into a furnace at the rate of 1.7 Kg (3.7 pounds) per hour using gas at the rate of 4.2 m³ (147 cubic feet) per hour at a gas/air mixture which was approximately 22% excess gas. The resultant glass-sphere product had an average density of .611 grams per cubic centimeter at a yield of 92.5% by weight hollow spheres. This product was comprised of particles whose sizes broke down as follows: 90P = 25.7 µm; 10P = 10.0 µm; and 50P = 17.7 µm. Accordingly, its GQ was .89.

A hydrostatic test of this glass-sphere product produced only a 1.7% volume loss at 20.7 MPa (3000 psi), and only a 25% volume loss at 68.95 MPa (10,000 psi). By comparison, the strongest commercial product of comparable average density (.6 grams per cubic centimeter) had a percentage volume loss of 50% at 68.95 MPa (10,000 psi).

These same two products also were introduced into polymers subjected to injection molding on the same injection molder. The percentage of spheres breaking during this molding was insignificant for this glass-sphere product, but substantial for the commercial product.

EXAMPLE 4

A glass frit having the same chemical composition as Example 3 was ground to provide a breakdown of particle sizes as follows: 90P = 8.3 µm; 10P = 1.8 µm; and 50P = 4.8 µm. These particles were fed into a furnace at the rate of 1.53 Kg (3.4 pounds) per hour using gas at the rate of 3.3 m³ (115 cubic feet) per hour at a gas/air mixture which was approximately 12% excess gas. The resultant glass-sphere product had an average density of 1.10 grams per cubic centimeter at a yield of 43% by weight hollow glass spheres. This product was comprised of particles whose sizes broke down as follows: 90P = 13.7 µm; 10P = 4.0 µm; and 50P = 8.8 µm. Accordingly, its GQ was 1.10.

Hydrostatic pressure testing of this product produced only a 13% volume loss at 68.95 MPa (10,000 psi) and only a 30% volume loss at 137.9 MPa (20,000 psi).

The chemical durability and resistance to leaching of this product was determined by subjecting a sample to boiling deionized water under reflux for one hour and then testing the water for pH, conductivity, and content of total alkali, calcium, boron, and silica. For comparison, the same test was conducted on commercial soda-lime glass and a boro-

silicate

Total						
	pH	Conductivity (mho/cm)	Alkali (mg/cc)	Calcium (mg/cc)	Boron (mg/cc)	Silica (mg/cc)
Sample	8.3	52	8.3	7.1	7.0	0.4
Soda-Lime	9.4	101	25.7	18.1	trace	5.4
Glass	8.5	45	3.6	20.4	18.7	1.1
Boro-silicate						
Glass						

These results demonstrate that the overall chemical resistance and durability of the hollow glass-sphere product exceeds that of these commercial glasses.

Thus, the present invention meets its objectives in providing a new chemical composition for hollow glass spheres. This composition produces hollow spheres having high strength, yield and chemical durability. The average densities of these spheres can range from .10 grams per cubic centimeter to 2.0 grams per cubic centimeter. The strength of these hollow glass spheres is further enhanced through an optimum selection of particle sizes.

The terms and expressions which have been employed herein are used as terms of description and not of limitation, and there is no intention in the use of such terms and expressions to exclude any equivalents of the features described or of portions thereof, it being recognized that various modifications are possible within the scope of the invention.

Claims

1. Durable high-strength hollow glass spheres made by heating solid glass particles, said spheres having an average density of approximately 0.10 grams/cc to approximately 2.0 grams/cc and consisting essentially of the following ingredients in the following amounts stated as weight percentages:

SiO ₂	50.0-57.0
R ₂ O	2.0-15.0
B ₂ O ₃	0.0-20.0
S	0.05-1.5
RO	2.0-25.0
Al ₂ O ₃	0.0-10.0
P ₂ O ₅	0.0-5.0
F	0.0-5.0

wherein R₂O is Na₂O, K₂O or Li₂O and RO is CaO or ZnO.

2. Hollow glass spheres as in claim 1 wherein Na₂O, K₂O and Li₂O are present in weight percentages of 2.5 to 12.8, 3.8 to 10.0 and 1.0 to 3.0, respectively.
3. Hollow glass spheres as in claim 1 wherein Na₂O, K₂O and Li₂O are present in the amounts of approximately one part by weight Li₂O, to two parts by weight Na₂O, to three parts by weight K₂O, such that Li₂O, Na₂O and K₂O are included in the glass in a substantially molar balance.
4. Hollow glass spheres as in claim 1 wherein B₂O₃ is present in a weight percentage of 6.0 to 15.0.
5. Hollow glass spheres as in claim 1 wherein B₂O₃ is present in a weight percentage of 11.74 to 20.0.
6. Hollow glass spheres as in claim 1 wherein CaO and ZnO are present in weight percentages of 5.0 to 20.0 and 1.5 to 4.0, respectively.
7. Hollow glass spheres as in claim 1 wherein Al₂O₃ is present in a weight percentage of 2.0 to 7.0.

8. Hollow glass spheres as in claim 1 wherein P_2O_5 is present in a weight percentage of 0.5 to 4.0.

9. Hollow glass spheres as in claim 1 wherein F is present in a weight percentage of 1.5 to 2.5.

10. Hollow glass spheres as in claim 1 having a GQ of 0.8 to 1.3.

11. A product of durable high-strength hollow glass spheres and solid glass spheres made by heating solid glass particles, said product having an average density of approximately 0.10 grams/cc to approximately 2.0 grams/cc and consisting essentially of the following ingredients in the following amounts stated as weight percentages:

SiO_2	50.0-57.0
R_2O	2.0-15.0
B_2O_3	0.0-20.0
S	0.05-1.5
RO	2.0-25.0
Al_2O_3	0.0-10.0
P_2O_5	0.0-5.0
F	0.0-5.0

wherein R_2O is Na_2O , K_2O or Li_2O and RO is CaO or ZnO.

12. A product of glass spheres as in claim 11 wherein Na_2O , K_2O and Li_2O are present in weight percentages of 2.5 to 12.8, 3.8 to 10.0 and 1.0 to 3.0, respectively.

13. A product of glass spheres as in claim 11 wherein Na_2O , K_2O and Li_2O are present in the amounts of approximately one part by weight Li_2O , to two parts by weight Na_2O , to three parts by weight K_2O , such that Li_2O , Na_2O and K_2O are included in the glass in a substantially molar balance.

14. A product of glass spheres as in claim 11 wherein B_2O_3 is present in a weight percentage of 6.0 to 15.0.

15. A product of glass spheres as in claim 11 wherein B_2O_3 is present in a weight percentage of 11.74 to 20.0.

16. A product of glass spheres as in claim 15 wherein CaO and ZnO are present in weight percentages of 5.0 to 20.0 and 1.5 to 4.0, respectively.

17. A product of glass spheres as in claim 11 wherein Al_2O_3 is present in a weight percentage of 2.0 to 7.0.

18. A product of glass spheres as in claim 11 wherein P_2O_5 is present in a weight percentage of 0.5 to 4.0.

19. A product of glass spheres as in claim 11 wherein F is present in a weight percentage of 1.5 to 2.5.

20. A product of glass spheres as in claim 15 having a GQ of 0.8 to 1.3.

21. Durable high-strength hollow glass spheres made by heating solid glass particles, said spheres consisting essentially of the following ingredients in the following amounts stated as weight percentages:

SiO_2	50.0-57.0
Na_2O	2.5-12.8
K_2O	3.8-10.0
Li_2O	1.0-3.0
B_2O_3	6.0-15.0
S	0.05-1.5
CaO	5.0-20.0
ZnO	1.5-4.0

Continuation of the Table on the next page

(continued)

Al ₂ O ₃	2.0-7.0
P ₂ O ₅	0.5-4.0
F	1.5-2.5

22. Hollow glass spheres as in claim 21 wherein Na₂O, K₂O and Li₂O are present in the amounts of approximately one part by weight Li₂O, to two parts by weight Na₂O, to three parts by weight K₂O, such that Li₂O, Na₂O and K₂O are included in the glass in a substantially molar balance.

23. Hollow glass spheres as in claim 21 having a GQ of 0.8 to 1.3.

24. Hollow glass spheres as in claim 21 wherein B₂O₃ is present in a weight percentage of 11.74 to 15.0.

25. An article of manufacture comprising a polymeric compound and dispersed therein durable high-strength hollow glass spheres made by heating solid glass particles, said spheres having an average density of approximately 0.10 grams/cc to approximately 2.0 grams/cc and consisting essentially of the following ingredients in the following amounts stated as weight percentages:

SiO₂ 50.0-57.0

R₂O 2.0-15.0

B₂O₃ 0.0-20.0

S 0.05-1.5

RO 2.0-25.0

Al₂O₃ 0.0-10.0

P₂O₅ 0.0-5.0

F 0.0-5.0

wherein R₂O is Na₂O, K₂O or Li₂O and RO is CaO or ZnO.

26. An article of manufacture as in claim 35 wherein B₂O₃ is present in said spheres in a weight percentage of 11.74 to 20.0.

27. An article of manufacture comprising a polymeric compound and dispersed therein a product of durable high-strength hollow glass spheres and solid glass spheres made by heating solid glass particles, said products having an average density of approximately 0.10 grams/cc to approximately 2.0 grams /cc and consisting essentially of the following ingredients in the following amounts stated as weight percentages:

SiO ₂	50.0-57.0
R ₂ O	2.0-15.0
B ₂ O ₃	0.0-20.0
S	0.05-1.5
RO	2.0-25.0
Al ₂ O ₃	0.0-10.0
P ₂ O ₅	0.0-5.0
F	0.0-5.0

wherein R₂O is Na₂O, K₂O or Li₂O and RO is CaO or ZnO.

28. An article of manufacture as in claim 27 wherein B₂O₃ is present in said spheres in a weight percentage of 11.74

to 20.0.

29. An article of manufacture as in claim 27 wherein B_2O_3 is present in said spheres in a weight percentage of 11.74 to 15.0.

30. An article of manufacture as in one of the claims 27 to 29 having a GQ of 0.8 to 1.3.

31. An article of manufacture comprising a polymeric compound and durable high-strength hollow glass spheres made by heating solid glass particles, said spheres consisting essentially of the following ingredients in the following amounts stated as weight percentages:

SiO_2	50.0-57.0
Na_2O	2.0-12.8
K_2O	3.8-10.0
Li_2O	1.0-3.0
B_2O_3	6.0-15.0
S	0.05-1.5
CaO	5.0-20.0
ZnO	1.5-4.0
Al_2O_3	2.0-7.0
P_2O_5	0.5-4.0
F	1.5-2.5

Patentansprüche

1. Haltbare Hohlglaskugeln großer Stärke, die durch Aufheizen von massiven Glaspartikeln hergestellt sind, wobei besagte Kugeln eine durchschnittliche Dichte von ungefähr 0,10 Gramm/cc bis ungefähr 2,0 Gramm/cc aufweisen und im wesentlichen aus den folgenden Bestandteilen in den folgenden Mengen, die in Gewichtsprozenten angegeben sind, bestehen:

SiO_2	50,0-57,0
R_2O	2,0-15,0
B_2O_3	0,0-20,0
S	0,05-1,5
RO	2,0-25,0
Al_2O_3	0,0-10,0
P_2O_5	0,0-5,0
F	0,0-5,0,

wobei R_2O Na_2O , K_2O oder Li_2O ist und RO CaO oder ZnO ist.

2. Hohlglaskugeln nach Anspruch 1, dadurch gekennzeichnet, daß Na_2O , K_2O und Li_2O in Gewichtsprozenten von 2,5 bis 12,8, 3,8 bis 10,0 bzw. 1,0 bis 3,0 vorliegen.

3. Hohlglaskugeln nach Anspruch 1, dadurch gekennzeichnet, daß Na_2O , K_2O und Li_2O in Mengen von ungefähr einem Gewichtsteil Li_2O , zu zwei Gewichtsteilen Na_2O und zu drei Gewichtsteilen K_2O vorliegen, so daß Li_2O , Na_2O und K_2O in dem Glas in einem im wesentlichen molaren Gleichgewicht enthalten sind.

4. Hohlglaskugeln nach Anspruch 1, dadurch gekennzeichnet, daß B_2O_3 in 6,0 bis 15,0 Gewichtsprozent vorliegt.

5. Hohlglaskugeln nach Anspruch 1, dadurch gekennzeichnet, daß B_2O_3 in 11,74 bis 20,0 Gewichtsprozent vorliegt.

6. Hohlglaskugeln nach Anspruch 1, dadurch gekennzeichnet, daß CaO und ZnO in 5,0 bis 20,0 bzw. 1,5 bis 4,0 Gewichtsprozent vorliegen.

EP 0 430 995 B1

7. Hohlglaskugeln nach Anspruch 1, dadurch gekennzeichnet, daß Al_2O_3 in 2,0 bis 7,0 Gewichtsprozent vorliegt.
8. Hohlglaskugeln nach Anspruch 1, dadurch gekennzeichnet, daß P_2O_5 in 0,5 bis 4,0 Gewichtsprozent vorliegt.
- 5 9. Hohlglaskugeln nach Anspruch 1, dadurch gekennzeichnet, daß F in 1,5 bis 2,5 Gewichtsprozent vorliegt.
10. Hohlglaskugeln nach Anspruch 1, dadurch gekennzeichnet, daß sie ein GQ von 0,8 bis 1,3 aufweisen.

- 10 11. Produkt aus haltbaren Hohlglaskugeln großer Stärke und massiven Glaskugeln, die durch Aufheizen von massiven Glaspartikeln hergestellt sind, wobei besagtes Produkt eine durchschnittliche Dichte von ungefähr 0,10 Gramm/cc bis ungefähr 2,0 Gramm/cc aufweist und im wesentlichen aus folgenden Bestandteilen in den folgenden Mengen, die in Gewichtsprozenten angegeben sind, besteht:

15	SiO_2	50,0–57,0
	R_2O	2,0–15,0
	B_2O_3	0,0–20,0
	S	0,05–1,5
20	RO	2,0–25,0

25	Al_2O_3	0,0–10,0
	P_2O_5	0,0–5,0
	F	0,0–5,0,

wobei R_2O Na_2O , K_2O oder Li_2O ist und RO CaO oder ZnO ist.

- 30 12. Produkt aus Glaskugeln nach Anspruch 11, dadurch gekennzeichnet, daß Na_2O , K_2O und Li_2O in 2,0 bis 12,8, 3,8 bis 10,7 bzw. 1,0 bis 3,0 Gewichtsprozent vorliegen.
- 35 13. Produkt aus Glaskugeln nach Anspruch 11, dadurch gekennzeichnet, daß Na_2O , K_2O und Li_2O in Mengen von ungefähr einem Gewichtsteil Li_2O , zu zwei Gewichtsteilen Na_2O und zu drei Gewichtsteilen K_2O vorliegen, so daß Li_2O , Na_2O und K_2O in dem Glas in einem im wesentlichen molaren Gleichgewicht enthalten sind.
- 40 14. Produkt aus Glaskugeln nach Anspruch 11, dadurch gekennzeichnet, daß B_2O_3 in 6,0 bis 15,0 Gewichtsprozent vorliegt.
15. Produkt aus Glaskugeln nach Anspruch 11, dadurch gekennzeichnet, daß B_2O_3 in 11,74 bis 20,0 Gewichtsprozent vorliegt.
- 45 16. Produkt aus Glaskugeln nach Anspruch 15, dadurch gekennzeichnet, daß CaO und ZnO in 5,0 bis 20,0 bzw. 1,5 bis 4,0 Gewichtsprozent vorliegen.
17. Produkt aus Glaskugeln nach Anspruch 11, dadurch gekennzeichnet, daß Al_2O_3 in 2,0 bis 7,0 Gewichtsprozent vorliegt.
- 50 18. Produkt aus Glaskugeln nach Anspruch 11, dadurch gekennzeichnet, daß P_2O_5 in 0,5 bis 4,0 Gewichtsprozent vorliegt.
19. Produkt aus Glaskugeln nach Anspruch 11, dadurch gekennzeichnet, daß F in 1,5 bis 2,5 Gewichtsprozent vorliegt.
- 55 20. Produkt aus Glaskugeln nach Anspruch 15, dadurch gekennzeichnet, daß es ein GQ von 0,8 bis 1,3 aufweist.
21. Haltbare Hohlglaskugeln großer Stärke, die durch Aufheizen von massiven Glaspartikeln hergestellt sind, wobei die Kugeln im wesentlichen aus den folgenden Bestandteilen in den folgenden Mengen, die in Gewichtsprozenten

angegeben sind, bestehen:

5

10

15

SiO ₂	50,0-57,0
Na ₂ O	2,5-12,8
K ₂ O	3,8-10,0
Li ₂ O	1,0-3,0
B ₂ O ₃	6,0-15,0
S	0,05-1,5
CaO	5,0-20,0
ZnO	1,5-4,0
Al ₂ O ₃	2,0-7,0
P ₂ O ₅	0,5-4,0
F	1,5-2,5

22. Hohlglaskugeln nach Anspruch 21, dadurch gekennzeichnet, daß Na₂O, K₂O und Li₂O in Mengen von ungefähr einem Gewichtsteil Li₂O, zu zwei Gewichtsteilen Na₂O und zu drei Gewichtsteilen K₂O vorliegen, so daß Li₂O, Na₂O und K₂O in dem Glas in einem im wesentlichen molaren Gleichgewicht enthalten sind.

20

23. Hohlglaskugeln nach Anspruch 21, dadurch gekennzeichnet, daß sie ein GQ von 0,8 bis 1,3 aufweisen.

24. Hohlglaskugeln nach Anspruch 21, dadurch gekennzeichnet, daß B₂O₃ in 11,74 bis 15,0 Gewichtsprozent vorliegt.

25

25. Herstellungsartikel umfassend eine Polymerverbindung und darin dispergierte, haltbare Hohlglaskugeln großer Stärke, die durch Aufheizen von massiven Glasparkeln hergestellt sind, wobei besagte Kugeln eine durchschnittliche Dichte von ungefähr 0,10 Gramm/cc bis ungefähr 2,0 Gramm/cc aufweisen und im wesentlichen aus den folgenden Bestandteilen in den folgenden Mengen, die in Gewichtsprozenten angegeben sind, bestehen:

30

35

SiO ₂	50,0-57,0
R ₂ O	2,0-15,0
B ₂ O ₃	0,0-20,0
S	0,05-1,5
RO	2,0-25,0
Al ₂ O ₃	0,0-10,0
P ₂ O ₅	0,0-5,0
F	0,0-5,0

40

wobei R₂O Na₂O, K₂O oder Li₂O ist und RO CaO oder ZnO ist.

26. Herstellungsartikel nach Anspruch 25, dadurch gekennzeichnet, daß B₂O₃ in besagten Kugeln in 11,74 bis 20,0 Gewichtsprozent vorliegt.

45

27. Herstellungsartikel umfassend eine Polymerverbindung und darin dispergiert ein Produkt aus haltbaren Hohlglaskugeln großer Stärke und massiven Glaskugeln, die durch Aufheizen von massiven Glasteilchen hergestellt sind, wobei besagte Produkte eine durchschnittliche Dichte von ungefähr 0,10 Gramm/cc bis ungefähr 2,0 Gramm/cc aufweisen und im wesentlichen aus den folgenden Bestandteilen in den folgenden Mengen, die in Gewichtsprozenten angegeben sind, bestehen:

50

55

EP 0 430 995 B1

5	SiO_2	50,0-57,0
	R_2O	2,0-15,0
	B_2O_3	0,0-20,0
	S	0,05-1,5
10	RO	2,0-25,0
	Al_2O_3	0,0-10,0
15	P_2O_5	0,0-5,0
	F	0,0-5,0,

wobei R_2O Na_2O , K_2O oder Li_2O ist und RO CaO oder ZnO ist.

- 20 **28.** Herstellungsartikel nach Anspruch 27, dadurch gekennzeichnet, daß B_2O_3 in besagten Kugeln in 11,74 bis 20,0 Gewichtsprozent vorliegt.
- 29.** Herstellungsartikel nach Anspruch 27, dadurch gekennzeichnet, daß B_2O_3 in besagten Kugeln in 11,74 bis 15,0 Gewichtsprozent vorliegt.
- 25 **30.** Herstellungsartikel nach irgendeinem der Ansprüche 27 bis 29, dadurch gekennzeichnet, daß er ein GQ von 0,8 bis 1,3 aufweist.
- 30 **31.** Herstellungsartikel umfassend eine Polymerverbindung und haltbare Hohlglaskugeln großer Stärke, die durch Aufheizen von festen Glaspartikeln hergestellt sind, wobei besagte Kugeln im wesentlichen aus den folgenden Bestandteilen in den folgenden Mengen, die in Gewichtsprozenten angegeben sind, bestehen:

35	SiO_2	50,0-57,0
	Na_2O	2,0-12,8
	K_2O	3,8-10,0
	Li_2O	1,0-3,0
	B_2O_3	6,0-15,0
40	S	0,05-1,5
	CaO	5,0-20,0
	ZnO	1,5-4,0
	Al_2O_3	2,0-7,0
	P_2O_5	0,5-4,0
45	F	1,5-2,5.

Revendications

- 50 **1.** Sphères de verre creuses durables à grande résistance mécanique fabriquées en chauffant des particules de verre pleines, lesdites sphères ayant une masse volumique moyenne d'environ 0,10 g/cm³ à environ 2,0 g/cm³ et étant constituées essentiellement des ingrédients suivants en les quantités suivantes exprimées en pourcentages en poids :

55	SiO_2	50,0-57,0
	R_2O	2,0-15,0

Suite du Tableau sur la page suivante

EP 0 430 995 B1

(suite)

B ₂ O ₃	0,0-20,0
S	0,05-1,5
RO	2,0-25,0
Al ₂ O ₃	0,0-10,0
P ₂ O ₅	0,0-5,0
F	0,0-5,0

où R₂O est Na₂O, K₂O ou Li₂O et RO est CaO OU ZnO.

- Sphères de verre creuses selon la revendication 1, dans lesquelles Na₂O, K₂O et Li₂O sont présents en des pourcentages en poids de 2,5 à 12,8, 3,8 à 10,0 et 1,0 à 3,0, respectivement.

- Sphères de verre creuses selon la revendication 1, dans lesquelles Na₂O, K₂O et Li₂O sont présents en les quantités d'environ 1 partie en poids de Li₂O, pour 2 parties en poids de Na₂O, pour 3 parties en poids de K₂O, si bien que Li₂O, Na₂O et K₂O sont inclus dans le verre en des quantités molaires sensiblement égales.

- Sphères de verre creuses selon la revendication 1, dans lesquelles B₂O₃ est présent en un pourcentage en poids de 6,0 à 15,0.

- Sphères de verre creuses selon la revendication 1, dans lesquelles B₂O₃ est présent en un pourcentage en poids de 11,74 à 20,0.

- Sphères de verre creuses selon la revendication 1, dans lesquelles CaO et ZnO sont présents en des pourcentages en poids de 5,0 à 20,0 et 1,5 à 4,0, respectivement.

- Sphères de verre creuses selon la revendication 1, dans lesquelles Al₂O₃ est présent en un pourcentage en poids de 2,0 à 7,0.

- Sphères de verre creuses selon la revendication 1, dans lesquelles P₂O₅ est présent en un pourcentage en poids de 0,5 à 4,0.

- Sphères de verre creuses selon la revendication 1, dans lesquelles F est présent en un pourcentage en poids de 1,5 à 2,5.

- Sphères de verre creuses selon la revendication 1, ayant un QG de 0,8 à 1,3.

- Un produit de sphères de verre creuses durables à grande résistance mécanique et de sphères de verre pleines, fabriqué en chauffant des particules de verre pleines, ledit produit ayant une masse volumique moyenne d'environ 0,10 g/cm³ à environ 2,0 g/cm³ et étant constitué essentiellement des ingrédients suivants en les quantités suivantes exprimées en pourcentages en poids :

SiO ₂	50,0-57,0
R ₂ O	2,0-15,0
B ₂ O ₃	0,0-20,0
S	0,05-1,5
RO	2,0-25,0
Al ₂ O ₃	0,0-10,0
P ₂ O ₅	0,0-5,0
F	0,0-5,0

où R₂O est Na₂O, K₂O ou Li₂O et RO est CaO ou ZnO.

- Un produit de sphères de verre selon la revendication 11, dans lequel Na₂O, K₂O et Li₂O sont présents en des pourcentages en poids de 2,5 à 12,8, 3,8 à 10,0 et 1,0 à 3,0, respectivement.

EP 0 430 995 B1

13. Un produit de sphères de verre selon la revendication 11, dans lequel Na_2O , K_2O et Li_2O sont présents en les quantités d'environ 1 partie en poids de Li_2O , pour 2 parties en poids de Na_2O , pour 3 parties en poids de K_2O , si bien que Li_2O , Na_2O et K_2O sont inclus dans le verre en des quantités molaires sensiblement égales.

14. Un produit de sphères de verre selon la revendication 11, dans lequel B_2O_3 est présent en un pourcentage en poids de 6,0 à 15,0.

15. Un produit de sphères de verre selon la revendication 11, dans lequel B_2O_3 est présent en un pourcentage en poids de 11,74 à 20,0.

16. Un produit de sphères de verre selon la revendication 15, dans lequel CaO et ZnO sont présents en des pourcentages en poids de 5,0 à 20,0 et 1,5 à 4,0, respectivement.

17. Un produit de sphères de verre selon la revendication 11, dans lequel Al_2O_3 est présent en un pourcentage en poids de 2,0 à 7,0.

18. Un produit de sphères de verre selon la revendication 11, dans lequel P_2O_5 est présent en un pourcentage en poids de 0,5 à 4,0.

19. Un produit de sphères de verre selon la revendication 11, dans lequel F est présent en un pourcentage en poids de 1,5 à 2,5.

20. Un produit de sphères de verre selon la revendication 15, ayant un QG de 0,8 à 1,3.

21. Sphères de verre creuses durables à grande résistance mécanique fabriquées en chauffant des particules de verre pleines, lesdites sphères étant constituée essentiellement des ingrédients suivants en les quantités suivantes exprimées en pourcentages en poids :

SiO_2	50,0-57,0
Na_2O	2,5-12,8
K_2O	3,8-10,0
Li_2O	1,0-3,0
B_2O_3	6,0-15,0
S	0,05-1,5
CaO	5,0-20,0
ZnO	1,5-4,0
Al_2O_3	2,0-7,0
P_2O_5	0,5-4,0
F	1,5-2,5

22. Sphères de verre creuses selon la revendication 21, dans lesquelles Na_2O , K_2O et Li_2O sont présents en les quantités d'environ 1 partie en poids de Li_2O , pour 2 parties en poids de Na_2O , pour 3 parties en poids de K_2O , si bien que Li_2O , Na_2O et K_2O sont incluse dans le verre en des quantités molaires sensiblement égales.

23. Sphères de verre creuses selon la revendication 21, ayant un QG de 0,8 à 1,3.

24. sphères de verre creuses selon la revendication 21, dans lesquelles B_2O_3 est présent en un pourcentage en poids de 11,74 à 15,0.

25. Un article manufacturé comprenant un composé polymère dans lequel sont dispersées des sphères de verre creuses durables à grande résistance mécanique fabriquées en chauffant des particules de verre pleines, lesdites sphères ayant une masse volumique moyenne d'environ 0,10 g/cm^3 à environ 2,0 g/cm^3 et étant essentiellement constituées des ingrédients suivants en les quantités suivantes exprimées en pourcentages en poids :

SiO_2	50,0-57,0
----------------	-----------

Suite du Tableau sur la page suivante

EP 0 430 995 B1

(suite)

R ₂ O	2,0-15,0
B ₂ O ₃	0,0-20,0
S	0,05-1,5
RO	2,0-25,0
Al ₂ O ₃	0,0-10,0
P ₂ O ₅	0,0-5,0
F	0,0-5,0

où R₂O est Na₂O, K₂O ou Li₂O et RO est CaO ou ZnO.

26. Un article manufacturé selon la revendication 25, dans lequel B₂O₃ est présent dans lesdites sphères en un pourcentage en poids de 11,74 à 20,0.

27. Un article manufacturé comprenant un composé polymère dans lequel est dispersé un produit de sphères de verre creuses durables à grande résistance mécanique et de sphères de verre pleines fabriqué en chauffant des particules de verre pleines, ledit produit ayant une masse volumique moyenne d'environ 0,10 g/cm³ à environ 2,0 g/cm³ et étant constitué essentiellement des ingrédients suivants en les quantités suivantes exprimées en pourcentages en poids :

SiO ₂	50,0-57,0
R ₂ O	2,0-15,0
B ₂ O ₃	0,0-20,0
S	0,05-1,5
RO	2,0-25,0
Al ₂ O ₃	0,0-10,0
P ₂ O ₅	0,0-5,0
F	0,0-5,0

où R₂O est Na₂O, K₂O ou Li₂O et RO est CaO ou ZnO.

28. Un article manufacturé selon la revendication 27, dans lequel B₂O₃ est présent dans lesdites sphères en un pourcentage en poids de 11,74 à 20,0.

29. Un article manufacturé selon la revendication 27, dans lequel B₂O₃ est présent dans lesdites sphères en un pourcentage en poids de 11,74 à 15,0.

30. Un article manufacturé selon l'une des revendications 27 à 29, ayant un QG de 0,8 à 1,3.

31. Un article manufacturé comprenant un composé polymère et des sphères de verre creuses durables à grande résistance mécanique fabriquées en chauffant des particules de verre pleines, lesdites sphères étant constituées essentiellement des ingrédients suivants en les quantités suivantes exprimées en pourcentages en poids :

SiO ₂	50,0-57,0
Na ₂ O	2,0-12,8
K ₂ O	3,8-10,0
Li ₂ O	1,0-3,0
B ₂ O ₃	6,0-15,0
S	0,05-1,5
CaO	5,0-20,0
ZnO	1,5-4,0
Al ₂ O ₃	2,0-7,0
P ₂ O ₅	0,5-4,0
F	1,5-2,5